

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 42	501
CLIENT REFERENCE	CPC/DPL/159 20/8/25	
SAMPLE	CEM II A-L 42.5R	
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	27-Aug-25	
DATE OF TESTS	27-Aug-25	to 24-Sep-25
DATE OF REPORT	24-Sep-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	220 mins	(BS EN 196-3:2016)
----------------------	----------	--------------------


COMPRESSIVE STRENGTH: MORTAR PRISMS (BS EN 196-1:2016).

AT 2 DAYS	30.1 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	57.1 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	n/a %	(BS EN 196-2:2013)
INSOLUBLE RESIDUE	n/a %	(BS EN 196-2:2013)
SULPHATE	3.16 %	(BS EN 196-2:2013)

END OF REPORT

SIGNED:.....

Certificate signed by: **S.Sykes**
Senior Technician