

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 52	494
CLIENT REFERENCE	CPC/DAC/130- 25 07-5-25	
SAMPLE	52.5N	SANTANDER
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	12-May-25	
DATE OF TESTS	12-May-25	to 09-Jun-25
DATE OF REPORT	09-Jun-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	167 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	41.0 MPa	(Mean of 6 results,none discarded)
AT 28 DAYS	64.3 MPa	(Mean of 6 results,none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	2.30 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	1.84 %	(BSEN 196-2:2013)
SULPHATE	3.30 %	(BSEN 196-2:2013)

END OF REPORT



SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician