

## TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 52	514
CLIENT REFERENCE	CPC/DPL/178 23/10/25	
SAMPLE	52.5N	SANTANDER
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	30-Oct-25	
DATE OF TESTS	30-Oct-25	to 27-Nov-25
DATE OF REPORT	28-Nov-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

### INITIAL SETTING TIME

INITIAL SETTING TIME	151 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

### COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	38.4 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	64.5 MPa	(Mean of 6 results, none discarded)

### CHEMICAL COMPOSITION :- by mass, as received

LOI	3.00 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	0.74 %	(BSEN 196-2:2013)
SULPHATE	3.32 %	(BSEN 196-2:2013)

END OF REPORT



SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician