

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 52	516
CLIENT REFERENCE	CPC/DAC/184 12/11/25	
SAMPLE	52.5N	SANTANDER
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	25-Nov-25	
DATE OF TESTS	25-Nov-25	to 23-Dec-25
DATE OF REPORT	06-Jan-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	157 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	36.1 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	63.6 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	3.52 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	0.74 %	(BSEN 196-2:2013)
SULPHATE	3.15 %	(BSEN 196-2:2013)

END OF REPORT



SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician