

## TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 52	519
CLIENT REFERENCE	CPC/DAC 187 26/11/25	
SAMPLE	52.5N	SANTANDER
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	28-Nov-25	
DATE OF TESTS	28-Nov-25	to 26-Dec-25
DATE OF REPORT	06-Jan-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

### INITIAL SETTING TIME

INITIAL SETTING TIME	177 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

### COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	34.0 MPa	(Mean of 6 results, none discarded)
-----------	----------	-------------------------------------

AT 28 DAYS	64.0 MPa	(Mean of 6 results, none discarded)
------------	----------	-------------------------------------

### CHEMICAL COMPOSITION :- by mass, as received

LOI	3.69 %	(BSEN 196-2:2013)
-----	--------	-------------------

INSOLUBLE RESIDUE	0.49 %	(BSEN 196-2:2013)
-------------------	--------	-------------------

SULPHATE	3.14 %	(BSEN 196-2:2013)
----------	--------	-------------------

END OF REPORT



SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician