

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 52	520
CLIENT REFERENCE	CPC/DAC 190 3/12/25	
SAMPLE	52.5N	SANTANDER
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	09-Dec-25	
DATE OF TESTS	09-Dec-25	to 06-Jan-26
DATE OF REPORT	06-Jan-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	146 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	32.5 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	64.2 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	2.93 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	0.57 %	(BSEN 196-2:2013)
SULPHATE	3.20 %	(BSEN 196-2:2013)

END OF REPORT



SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician