

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 52	547
CLIENT REFERENCE	CPC/DAC/250 23/7/26	
SAMPLE	52.5N	MATAPORQUERA
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	24-Jul-26	
DATE OF TESTS	27-Jul-26	to 24-Aug-26
DATE OF REPORT	25-Aug-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	214 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	35.1 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	65.7 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	2.99 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	0.32 %	(BSEN 196-2:2013)
SULPHATE	3.32 %	(BSEN 196-2:2013)

END OF REPORT



SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician