

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 52	548
CLIENT REFERENCE	CPC/DAC/252 29/7/26	
SAMPLE	52.5N	MATAPORQUERA
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	31-Jul-26	
DATE OF TESTS	31-Jul-26	to 28-Aug-26
DATE OF REPORT	01-Sep-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	201 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	40.2 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	65.4 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	2.90 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	0.37 %	(BSEN 196-2:2013)
SULPHATE	3.04 %	(BSEN 196-2:2013)

END OF REPORT



SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician