

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 52	521
CLIENT REFERENCE	CPC/DAC/192 SILO 2 10/12/25	
SAMPLE	52.5N	SANTANDER
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	12-Dec-25	
DATE OF TESTS	15-Dec-25	to 12-Jan-26
DATE OF REPORT	14-Jan-26	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	207 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	33.6 MPa	(Mean of 6 results, none discarded)
-----------	----------	-------------------------------------

AT 28 DAYS	62.2 MPa	(Mean of 6 results, none discarded)
------------	----------	-------------------------------------

CHEMICAL COMPOSITION :- by mass, as received

LOI	4.07 %	(BSEN 196-2:2013)
-----	--------	-------------------

INSOLUBLE RESIDUE	0.67 %	(BSEN 196-2:2013)
-------------------	--------	-------------------

SULPHATE	3.12 %	(BSEN 196-2:2013)
----------	--------	-------------------

END OF REPORT



SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician