

TEST REPORT PREPARED FOR DRAGON CEMENT

REPORT REFERENCE	DG 52	495
CLIENT REFERENCE	CPC/DAC/131- 25 14-5-25	
SAMPLE	52.5N	SANTANDER
SAND	GERMAN	
DATE OF RECEIPT OF SAMPLE	16-May-25	
DATE OF TESTS	19-May-25	to 16-Jun-25
DATE OF REPORT	16-Jun-25	

ALL RESULTS RELATE ONLY TO SAMPLE TESTED

INITIAL SETTING TIME

INITIAL SETTING TIME	177 mins	(BSEN 196-3:2016)
----------------------	----------	-------------------

COMPRESSIVE STRENGTH: MORTAR PRISMS (BSEN 196-1:2016).

AT 2 DAYS	40.3 MPa	(Mean of 6 results, none discarded)
AT 28 DAYS	69.1 MPa	(Mean of 6 results, none discarded)

CHEMICAL COMPOSITION :- by mass, as received

LOI	3.08 %	(BSEN 196-2:2013)
INSOLUBLE RESIDUE	0.62 %	(BSEN 196-2:2013)
SULPHATE	3.21 %	(BSEN 196-2:2013)

END OF REPORT



SIGNED:.....

Certificate signed by:

S.Sykes

Senior Technician