

Product Data Sheet

Multilith Amber MP 0 Grease

Multipurpose Lithium EP Grease NLGI 0

Description

Multilith Amber MP 0 Grease is a high quality semi-fluid general purpose industrial lithium soap grease. It is amber in colour and has been formulated to provide extra protection against wear, rusting and water washout.

Multilith Amber MP 0 Grease is blended using premium selected base stocks, extreme pressure agents, oxidation, corrosion and wear inhibitors, and provides excellent water resistance, and wear protection.

Multilith Amber MP 0 Grease is a self-levelling grease and provides excellent oxidation and thermal stability to enhance grease life.

It provides excellent protection against rust and corrosion and resists water washout making it particularly suitable for extending bearing life in wet environments.

Applications

Multilith Amber MP 0 Grease is recommended for a wide variety of automotive and industrial greasing applications across many industries where a grease of NLGI 0 consistency is required.

It is suitable for plain bearings, rolling element bearings, gears and couplings where an NLGI 0 grease is required.

It can also be used in centralised and automated lubrication systems found in many industries including off-road construction, mining and quarry operations, road construction, agriculture and farming equipment, on-highway truck and trailer lubrication applications, including many automated truck greasing systems, and is an ideal choice where a self - levelling grease is required for sealed wheel hubs on truck and trailers.

Package Sizes

 Item Code
 Pack Size

 MG0410001-0180
 180 kg drum

 MG0410001-0020
 20kg pail

 MG0410001-0450
 450g cartridge

 (12 x 450g / ctn)

NOTE: Always confirm that the product selected is consistent with the original equipment manufacturer's recommendation for the equipment operating conditions and customer's maintenance practices.



Product Data Sheet

Key Benefits

- > Excellent oxidation and thermal stability
- > Excellent extreme pressure and load carrying performance and resistance to wear
- Good mechanical and shear stability
- > Excellent rust and corrosion resistance and resistance to water washout.
- > Good low temperature pumpability and performance in centralised systems

Typical Test Data

| Property | Method | Typical |
|--|------------|-------------------------------------|
| NLGI Grade | | 0 |
| Thickener Type | | Lithium 12- hydroxystearate soap |
| Colour, Visual | | Amber – Smooth |
| Corrosion, Cu strip, 24hr @100°C | ASTM D130 | 1b |
| Penetration, Worked, 25° C, | ASTM D217 | 368 |
| Dropping Point, °C, | ASTM D2265 | 190 |
| Base Oil Viscosity, cSt @ 40° C | ASTM D445 | 192.5 |
| 4-Ball Wear Test, scar, mm | ASTM D2266 | 0.42 |
| 4-Ball EP Weld Point, kgf | ASTM D2596 | 250 |
| Timken OK Load, kg | ASTM D2509 | 20 |
| | | |
| Usable temperature range in continuous service | | -25 to 130°C |
| Maximum temperature for short term exposure | | 170°C |



Product Data Sheet

Storage and Handling

Wherever possible store this product under cover to avoid any ingress of water. Do not store near hot work areas or where temperatures can reach above 60° C.

Health, Safety and Environment

Based on available information, this product is not expected to produce adverse effects on health when used for the intended application and the recommendations provided in the Safety Data Sheet (SDS) are followed. This product should not be used for purposes other than its intended use.

Consult the Safety Data Sheet available by contacting The Millstream Group Pty Ltd office for further information.

Contact



The Millstream Group Pty Ltd 89 Bullock Dray Drive, Mt Crosby QLD 4306, Australia +61 447 310 335



E: enquiries@millstreamgroup.com.au / www.millstreamgroup.com.au

