

DM65A材料特性

DM65A Material Characteristics

项目 Item	符号 Symbol	条件 Condition	单位 Unit	DM65A
初始磁导率 Initial Permeability	μ_i	25°C		700 ± 25% (1KHz)
饱和磁通密度 Saturation flux density	Bs	25°C H=1600A/m	mT	260
剩磁 Remanence	Br	25°C	mT	210
矫顽力 Coercivity	Hc	25°C	A/m	45
居里温度 Curie temperature	Tc		°C	>110
电阻率 Electrical Resistivity	ρ	25°C	$\Omega \cdot m$	$>10^5$
密度 Density	d	25°C	g/cm^3	5.2

Hengdian Group DMEGC Magnetics Co.,Ltd