

材料特性

- 优异的直流叠加特性
- 低损耗
- 高效率、高功率密度

材料应用

- 光伏逆变器
- 新能源汽车
- 变频空调
- UPS 电源

Material Characteristics Parameter					
Characteristics	Parameter				
Material Grade	FH026	FH040	FH060	FH075	FH090
Initial Permeability	26	40	60	75	90
Bs (mT)	1100	1100	1100	1100	1100
Curie Temperature °C	>600	>600	>600	>600	>600
Temperature Range	-55~200	-55~200	-55~200	-55~200	-55~200
Core Loss (mw/cm ³) (50KHz/100mT)	650	500	500	500	500

