

Nylon 11 CF Powder

Carbon Fiber Reinforced, for Strong and Lightweight parts

Get the best of nylon and carbon fiber with this highly stable, high-performance material, perfect for end-use applications that require both high stiffness and superior strength and can take an impact.

Nylon 11 CF Powder is specifically developed for use on the Fuse 1+ 30W.

Functional composite prototypes

Tooling, Jigs, Fixtures

**Replacement and spare alternatives
to metal parts**

High-impact equipment



FLP11C01

Prepared 06/22/2022

Rev. 02 08/08/2023

To the best of our knowledge the information contained herein is accurate. However, Formlabs, Inc. makes no warranty, expressed or implied, regarding the accuracy of these results to be obtained from the use thereof.

Material Properties	METRIC ^{1,2}			IMPERIAL ^{1,2}			METHOD
	X	Y	Z	X	Y	Z	
Tensile Properties	METRIC ^{1,2}			IMPERIAL ^{1,2}			METHOD
Ultimate Tensile Strength	69 MPa	52 MPa	38 MPa	10 ksi	7.6 ksi	5.5 ksi	ASTM D638-14 Type 1
Tensile Modulus	5.3 GPa	2.8 GPa	1.6 GPa	770 ksi	410 ksi	240 ksi	ASTM D638-14 Type 1
Elongation at Break	9%	15%	5%	9%	15%	5%	ASTM D638-14 Type 1
Mechanical Properties	METRIC ^{1,2}			IMPERIAL ^{1,2}			METHOD
Flexural Strength	110 MPa			16 ksi			ASTM D790-15
Flexural Modulus	4.2 GPa			610 ksi			ASTM D790-15
Notched Izod	74 J/m			1.4 ft-lb/in			ASTM D256-10
Thermal Properties	METRIC ^{1,2}			IMPERIAL ^{1,2}			METHOD
Heat Deflection Temp. @ 1.8 MPa	178 °C			352 °F			ASTM D648-16
Heat Deflection Temp. @ 0.45 MPa	188 °C			370 °F			ASTM D648-16
Vicat Softening Temperature	188 °C			370 °F			ASTM D1525

Samples printed with Nylon 11 CF Powder have been evaluated in accordance with ISO 10993-1:2020 and is biologically safe for long term (>30 day) surface (intact skin) contacting devices. It has passed the requirements for the following biocompatibility risks:

ISO Standard	Description ^{3,4}
ISO 10993-5: 2009	Not cytotoxic
ISO 10993-23:2021	Not an irritant
ISO 10993-10:2021	Not a sensitizer

SOLVENT COMPATIBILITY

Percent weight gain over 24 hours for a printed and post-cured 1 x 1 x 1 cm cube immersed in respective solvent:

Solvent	24 hr weight gain, %	Solvent	24 hr weight gain, %
Acetic Acid 5%	0.2	Mineral oil, heavy	1.0
Acetone	0.2	Mineral oil, light	1.3
Bleach ~5% NaOCl	0.2	Salt Water (3.5% NaCl)	0.2
Butyl Acetate	0.2	Skydrol 5	0.8
Diesel Fuel	0.6	Sodium hydroxide solution (0.025% pH = 10)	0.2
Diethyl glycol monomethyl ether	0.5	Strong Acid (HCl Conc)	0.8
Hydraulic Oil	1.0	TPM	0.8
Hydrogen peroxide (3%)	0.2	Water	0.1
Isooctane	0.0	Xylene	0.2
Isopropyl Alcohol	0.2		

¹ Material properties may vary with part geometry, print orientation and temperature.

² Parts were printed using Fuse 1+ 30W, with Nylon 11 CF Powder. Parts were conditioned at 50% relative humidity and 23 °C for 7 days before testing.

³ Material properties may vary based on part design and manufacturing practices. It is the manufacturer's responsibility to validate the suitability of the printed parts for the intended use.

⁴ Nylon 11 CF Powder was tested at NAMSAs World Headquarters, OH, USA.